



# 聖騰股份有限公司

**SUN TALENT INDUSTRIAL CO., LTD.**

台中市西屯區福中九街 33 巷 15 號

NO.15, 33 LANE, FU CHUNG 9. STREET,

HIS TUN DIST, TAICHUNG, TAIWAN, REPUBLIC OF CHINA

TEL: (04) 23584333 FAX: (04) 23584796

E-mail : suntalen@ms7.hinet.net Website : www.suntalent.com.tw

## 橄欖砂

### 成份

#### SPECIFICATIONS

|                                |        |
|--------------------------------|--------|
| MgO                            | 42.66% |
| SiO <sub>2</sub>               | 40.28% |
| Al <sub>2</sub> O <sub>3</sub> | 0.75%  |
| Fe <sub>2</sub> O <sub>3</sub> | 8.97%  |
| CaO                            | 0.47%  |
| LOI                            | 0.92%  |

### 物理性質

|      |                             |
|------|-----------------------------|
| 耐火度  | 1680°C min                  |
| 莫氏硬度 | 6.5-7.0                     |
| PH   | 7.2-7.5                     |
| 體積密度 | 1.8                         |
| 比重   | 3.10-3.27 g/cm <sup>3</sup> |
| 壓力強度 | 2.0-3.0 mpa                 |

### 顆粒大小

30-50mesh 90%min    40-70mesh 90%min    200mesh 90%min